

PRODUCTION DESCRIPTION

A factory prepared mixture of Portland cement, polymer and aggregates for filling of joints 3 to 12mm for non absorbent tiles. For interior and exterior. It is durable, hard, colour fast & economical. It is suitable for grouting ceramic tiles, vitrified tiles, marbles, granites, mosaics and natural stone in walls and floors.

FEATURES

- It is recommended for use on tile joints of 1-6mm width.
- Ensure 24 hours time interval for grouting after tile fixing.
- Keep the grouted area free from dust particles for minimum 24 hours.
- For best results, use spacers and keep a minimum 2mm joint between tiles.
- If the tiles are highly porous. Do a sample test to check for possible staining. To avoid this problem, mask the tiles before grouting.

APPLICATION: Residential, Commercial, External Facades.

ADVANTAGES: For tile joints 3-12mm, uniform colour, Hard and durable, Economical.

MIXING RATIO: Used approximately 400ml of water or Home Pride Grout admix for 1 kg of Grout.

TECHNICAL DATA

Bulk Density 1.10-1.20gm/cc

| | | |
|--------------------------|---|-------------------------|
| Pot Life | : | Upto 1 Hour |
| Time to walk on | | |
| Grouted floor | : | 24 hours after grouting |
| Recommended tile | | |
| Joint width | : | 1 to 6mm |
| Site temperature at and | | |
| The time of application: | | between + 5*-35°C |
| Setting Time: | | |
| a) Initial | | 60-120 minutes |
| b) Final | | 160-220 minutes |
| Compressive strength | | |
| @28 days | | >16Mpa |

DIRECTION OF USE

SURFACE PREPARATION

- Clean and remove any loose particles.
- Make sure that the tiles joints are clean and saturated and excess water is removed from the joints before grouting.

APPLICATION

- Gradually add approximately 2.5 parts of powder to 1 part of clean water (measured by volume) and mix it to smooth, workable stiff paste.
- Do not attempt to extend the pot life by adding more water to the mix.
- Mix using a slow speed mixer.
- Completely fill the tile joints with the **HOME PRIDE SANDED GROUT** diagonally across the tile surfaces using a rubber grouting trowel or an appropriate tool.

HOME PRIDE SANDED GROUT



- Wait till **HOME PRIDE SANDED GROUT** has started to set (30 to 45 minutes).
- Remove excess grout using a sponge (45 to 60 minutes).
- After drying about 3 hours clean the tiles using a dry cloth.

COVERAGE: Varies with tiles size and grout width (Tile Length + Tile Breadth) X Tile Thickness X Joint width X Specific gravity=Kg/sq mtr Specific gravity =175 (The Length + Joint width) the breadth + joint width.

PACKAGING: 1Kg and 10Kg & 20Kg bags.

COLOUR: Available in all colours as per shade card.

SHELF LIFE: One year from the date of manufacturing for unopened bags, store in dry condition.

Availability

Home Pride Adhesive Pvt.Ltd
H-533, RIICO Industrial area, Ph-I
Bhiwadi,Distt. Alwar (Rajasthan)

Email: homeprideadhesive@gmail.com

www.homeprideadhesive.com

Price

Contact Home Pride Dealer in your area.

Technical Services

Home Pride Adhesive Pvt.Ltd

H-533, RIICO Industrial area, Ph-I
Bhiwadi,Distt. Alwar (Rajasthan)

HEALTH & SAFETY: HOME PRIDE SANDED GROUT is non –toxic. Use of gloves and goggles is recommended. Any splashes to skin or eyes should be waste off with clean water. In the event of prolonged irritation, medical advice should be sought. **HOME PRIDE** components are non flammable.