

HOME PRIDE

Complete Tile Fixing Solution



CEMENT GROUT SANDED


A FILLER USED FOR FILLING JOINTS OF 3MM TO 12MM FOR NON ABSORBENT TILES.



Latest Technology
Value For Money




Durability



Reliability



Resists Algae &
Fungus Growth





Description :-

Home Pride Cementitious grout is a factory prepared mixture of Portland cement, polymer and aggregates for filling of joints width 3 to 12 mm for non absorbent tiles. For interior and exterior . it is durable , hard, colour fast and economical .

Home Pride Grout (Sanded) filling Joint width	3 mm – 12 mm
--	--------------

Application :-

Home Pride cementitious grout is applicable on

- Residential
- Commercial
- Institution
- Hospital
- Schools.
- External Facades

Advantages :-

- ❖ Easy to maintenance
- ❖ Non shrinking and non cracking for tile joint 3mm - 12 mm
- ❖ Hard and durable
- ❖ Economic
- ❖ High ultimate strength and low permeability ensure the durability of the hardened grout.
- ❖ Available in a range of exciting colors that should satisfy even the most discriminating tastes.

Home Pride Cementitious Grout (Sanded)

Standard Compliance :-

Home Pride Cementitious Grout meet or exceeds the test requirements of ANSI A118.6.

Technical Data :-

The following results were obtained when mixed with water under laboratory working conditions (Temperature 21°C, 70°F).

Test Method	REQUIREMENT
Compressive Strength ANSI A 118.6 4.5	3500-4500psi(24.1 – 31 MPa)
Linear Shrinkage ANSI A118.6 4.3	<0.2 %
Water Absorption	5 – 6%

*Specification subject to change without notification .results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods & site conditions.

Working Properties	
Pot Life	2 hr
Foot Traffic	12 hr
Heavy Traffic	24 hr
Wet density	1.76 g/ml
Coverage	See Grout color chart for coverage information (Varies with tile size and grout width)

* Data sheets are subject to change without notice . for latest revision

Colour - Available in all colour as per shade card



Packaging :- 1kg , 10 kg ,20 kg bags .

Performance Specification :-

Grouting must be carried out with a pre-packaged cement based product.

It shall be mixed with clean water to the required quantity .the plastic grout must not bleed or segregate.

The storage , handling and placement of the grout must be in strict accordance with the manufacture instructions.

2-Mixing :-

Place the water in a clean mixing container and add grout powder slowly. mix by hand or with slow speed mixer . For best results a mechanically powered grout mixer (low speed drill fitted with a mixing paddle) should be used .when quantities up to 20 kg . To enable the grouting operation to be carried out continuously .it is essential that sufficient mixing capacity and labour are available.

Consistency of grout mix :-

The quantity of clean water required to be added to a 1 kg bag to achieve the desired consistency is given bellow

Grout	Water
1 Kg	350 ml -400 ml

Instruction for Application :-

Surface Preparation

Before starting to grout , remove spacers and debris in grout joints and remove dust and dirt using a wet sponge. Do not leave water standing in joints . substrate temperature must be between 4 °C to 32°C . apply grout release or sealer if necessary.

Application :-

Mixed grout put on grouting joints of tile and spread with a sparp ,firm rubber grout flout. Fill the grout past into the grouting joints until completely filled. Use diagonal strokes to pack the joints.

Base plate

Cleaning :-

Grout Primary Cleaning – remove excess grout from the face of the tiles with edge of the float . hold the float at 90° angle and pull it at a 45° angle diagonally across and tile to avoid pulling out the material.

Grout secondary cleaning – remove remaining grout with a damp sponge (not wet) or a damp towel. Work diagonally to the joints. Allow to dry . when the grout joints are firm , polish the surface with a coarse nylon pad ,cloth and minimal water .

Note – use caution when polishing soft glazed tiles or polished stone.

Storage :-

Home Pride Cementitious grout has a shelf life of 12 months if kept in a dry store in sealed bags. If stored in high temperature and high humidity location the shelf life will be reduced.

Health & Safety Precautions :-

Home Pride Cementitious grout is alkaline and should not come in to contact with skin and eyes.
Avoid inhalation of dust during mixing.



- ❖ Gloves ,Goggles and Dust mask should be worn.
- ❖ Avoid eye contact and prolong contact with skin .
- ❖ Wash thoroughly after handling.
- ❖ If eye contact occurs flesh with water for 15 minutes and consult with physician.
- ❖ Do not breath dust ; wear a P2 type respiratory mask

Fire :-

Home Pride Cementitious grout is Non – Flammable.

Additional information :-

Home Pride a wide rang of complementary products which include:

Adhesive for Glass Mosaic ,Adhesive for wall tile /Stone , Adhesive for AAC Blocks ,Admixtures , Epoxy grouts , Floor Hardener , Floor Tile Cleaner Etc.

CUSTOMER CARE:-

Home Pride Adhesive .Pvt.Ltd.

F.429,Phase-1 , RIICO Industrial area , Bhiwadi (Alwar, Raj.)

Branch Office M/s Home Pride Adhesive .Pvt.Ltd

Pole no. 1896 – 1897 , New Mandoli Industrial Area Delhi – 110093

Website : www.homepride.in

E-Mail . : homeprideadhesive@gmail.com

Mob. No -9810470965 , 9887723198,9917245684 .

Toll free : 1800 111 818